COECRETE 630 (0.2~0.4mm)


砂浆罩面 SEALER

COECRETE 630 (0.2~0.4mm) 是水性聚氨酯砂浆罩面,具有极佳的 耐磨性、耐化学品性及耐其它物理应力的性能。该产品使用在对地坪 要求比较高的场所,尤其是潮湿环境。涂膜的平整度、可呼吸功能、优 异的耐化学品及机械性能、耐温性使该产品能满足所有客户的要求,完全符合当地相关卫生及安全法规。

COECRETE 630 (0.2~0.4mm) is a flooring topcoat consisting of a water-based polyurethane resin dispersion modified with cement and size-graded aggregates and featuring an excellent resistance to abrasion, chemical aggression and other types of physical stress. It is used in areas where maximum performance is required



from a resin floor, including in damp environments in particular. Its surface flatness, breathability, extremely high chemical resistance and excellent mechanical properties, together with the possibility of conducting high-temperature sanitisation treatments, allow this system to meet the requirements of all customers, in compliance with all applicable legislation and local health and safety regulations.










聚氨酯砂浆系统

	步骤 Step	产品 Product	说明 Information	理论用量 Consumption	施工方法 Application method	覆涂间隔时间 Overcoating
1	基面 Base	处理 Preparation	机械处理,切锚固槽 Mechanical treatment, saw cut anchor grooves			
2	底涂 Primer	COEPOX 111/120	无溶剂环氧树脂 Solvent-free epoxy resin primer	0.5 kg/m²	滚涂 Roller	16小时后
3	撒播 Broadcast	石英砂 QUARTZ 0.7-1.2	在刚施工好的底涂上播撒石英砂 Sparse broadcast of quartz on freshly- applied primer	1.5 kg/m²	用手播撒 Scatter by hand	Allow 16 hours
4	砂浆层 Mortar	COECRETE 610 COECRETE 620	聚氨酯砂浆 Cement-modified polyurethane resin coating	1.9 kg/m²/mm 2.1 kg/m²/mm	镘涂 Trowel	24小时后 Allow 24 hours
5	罩面 Topcoat	COECRETE 630	聚氨酯砂浆罩面 Cement-modified polyurethane resin topcoat	0.3 kg/m²		



适用场所

- 食品、鱼肉类产业
- ■食品加工厂
- 饮料工业
- 化学工业
- = 定制加工厂
- 啤酒厂、乳制品/面食/饼干加工厂
- 屠宰业

Uses

- Food, meat and fish industry
- Food processing industry
- Beverage industry
- Chemical industry
- Custom work manufacturers
- Breweries, dairy factories, pasta manufacturers, biscuit factories
- Slaughtering industry