



COEPUR 720 (2~3mm)

弹性聚氨酯装饰地坪

ELASTIC POLYURETHANE DECORATIVE FLOOR

COEPUR 720 (2~3mm) 是双组份无溶剂弹性聚氨酯自流平系统, 是商业项目地面的理想选择, 静音, 抗裂, 装饰性佳, 耐磨, 易清洗。

COEPUR 720 (2~3mm) is a two-component solvent-free elastic self-levelling polyurethane system which is ideal to coat commercial floors. Just 2~3mm thick and requiring only a few days work, this system allows to create an anti-noise, anti-crack, pleasant flooring that is resistant to wear and compression and is easy to clean.

适用场所 Applications

- > 酿酒工业 Wine industry
- > 食品及食品加工行业 Food and food processing industry
- > 超市 Supermarkets
- > 医院 Hospitals
- > 制药工业 Pharmaceutical industry
- > 屠宰业, 鱼肉加工业
Slaughtering industry and meat and fish processing industry
- > 化学工业 Chemical industry
- > 行车频繁区域如汽修厂及汽车库
Garages and vehicle depots subjected to medium-to-heavy traffic
- > 食堂 Canteens
- > 轻工业 Light engineering industry
- > 展会、交易会 Exhibition and trade fair halls
- > 贮藏库 Storage depots

弹性抗裂
Elastic, crack-bridging
美观
Aesthetic
静音
Anti-noise
耐磨
Wear-resistant

技术标准 Technical standard

拉伸强度 Tensile strength	≥0.7MPa
断裂延伸率 Elongation at break	180%
压缩复原率 Compression recovery rate	≥95%
回弹值 Rebound value	≥20%
阻燃值 Flame retardant value	1级 Class 1
抗滑值 Anti slip value (BPN 20°C)	≥47
邵氏硬度 (D型) Shore hardness (Type D)	70-80

步骤 Step	产品 Product	说明 Information	理论用量 Consumption	施工方法 Application method	覆涂间隔时间 Overcoating
基面 Substrate	处理 Preparation	机械处理, 清洁 Mechanical treatment and cleaning of base	/	/	/
底涂 Primer	COEPOX 111 / 120	无溶剂环氧底涂 Solvent-free epoxy resin primer	0.3kg/m ²	滚涂 Roller	16小时后 Allow 16 hours
自流平 Self-levelling	COEPUR 720	弹性聚氨酯自流平 Elastic polyurethane self-levelling	2.0~3.0kg/m ²	镘涂 Trowel	24小时后 Allow 24 hours
着色层+彩片 (可选) Colored coat + Color chips (optional)	COEPUR W700	水性聚氨酯罩面 Water-based polyurethane topcoat	0.1kg/m ²	滚涂 + 用手播撒 Roller + Scatter by hand	24小时后 Allow 24 hours
透明罩面 Transparent topcoat	COEPUR W700	水性聚氨酯罩面 Water-based polyurethane topcoat	0.1kg/m ²	滚涂 Roller	/

